

① 8 mm ipasol neutral 70/37 pos.2 Thermally toughened ② 16 mm Argon 90% ③ 6 mm Planibel Clearlite Thermally toughened ④ 16 mm Argon 90% ⑤ Stratobel 55.4 (5 mm iplus 1.1 pos.5 + 1.52 mm PVB Clear + 5 mm Planibel Clearlite) Heat strengthened

Glass performance data simulation

☀️ Light properties - EN 410

Light transmittance : τ_v [%]	61
External light reflection : p_v [%]	14
Internal light reflection : p_{vi} [%]	17
Colour rendering index : R_a [%]	93

🔥 Energy properties - EN 410

Total solar energy transmittance : g [%]	34
External energy reflection : p_e [%]	35
Internal energy reflection : p_{ei} [%]	27
Direct energy transmission : τ_e [%]	27
Energy absorption glass 1 : ae_1 [%]	31
Energy absorption glass 2 : ae_2 [%]	2
Energy absorption glass 3 : ae_3 [%]	5
Total energy absorption : ae [%]	38
Shading coefficient : SC	0.39
UV transmission : τ_{uv} [%]	0
Selectivity	1.79

🌿 ENVIRONMENTAL PROPERTIES

Cradle to Gate – Global warming potential: Module A1-A3 : [kg CO ₂ eq. /m ²] ¹	NPD
--	-----

🌡️ Thermal properties - EN 673

Thermal transmittance (vertical glazing) : U value [W/(m ² .K)]	0.5
--	-----

🔊 Acoustic properties

Direct airborne sound reduction - Interpolated : R_w (C;Ctr) [dB] ²	43 (-2;-4)
--	------------

🛡️ Safety properties

Resistance to fire - EN 13501-2	NPD
Reaction to fire - EN 13501-1	NPD
Bullet resistance - EN 1063	NPD
Burglar resistance - EN 356	NPD
Pendulum body impact resistance - EN 12600	1C2 / 1C2 / NPD
Explosion resistance - EN 13541	NPD

📏 Thickness and weight

Nominal thickness : [mm]	57.5
Weight : [kg/m ²]	62

¹. This value represents a self-declared estimate of the Global Warming Potential (GWP) associated with the production of the configured glass product. This value covers the entire production phase but no other stage of the life cycle of the product is included in this value. The data used to estimate the environmental impact is representative of all AGC Glass Europe production in Europe. AGC Glass Europe has followed the modeling principles of the European standard EN 15804+A2, although no third-party verification has been carried out.

². The sound reduction indexes are interpolated (no test available). They correspond to glazing with dimensions 1230 mm by 1480 mm according to EN ISO 10140-3. In-situ performances may vary according to the effective glazing dimensions, supporting system, installation, environment, noise sources etc. The accuracy of the given indexes is +V/- 2 dB.



Glass Configurator
Calculation software verified by INISMA
EN 410 and EN 673
Report n° 2018B COU 35741



Several AGC products are now available in Low-Carbon Glass version. The Low-Carbon Glass version does not affect the properties of the above glass configuration. For more info about the AGC Low-Carbon Glass range, please visit our YourGlass page.

The AGC Glass Configurator is a simulation tool providing a performance analysis for the limited purpose of assisting the user in evaluating the performance of the glass configuration identified in this report. The interpolated performance is only applicable for glass products manufactured or processed by AGC. It does not replace an official Declaration of Performance and therefore may contain some variations, although AGC has made every effort to verify the reliability of this simulation tool. The user assumes any risk relating to the results provided by the tool and is solely responsible for the selection of the appropriate glass configuration for the user's application. This document is for informative purposes only and in no way implies acceptance of any order by the AGC Group. Please consult the Specific Conditions of Use <https://www.agc-yourglass.com/configurator/en/specific-conditions-of-use/> for the calculation standards that are used, the INISMA test report number and the accuracy of the values.

AGC makes no express or implied warranty of any kind with respect to the Glass Configurator. There are no warranties of merchantability, non-infringement or fitness for any particular purpose and no warranty shall be implied by operation of law or otherwise. In no event shall AGC be liable for direct, indirect, consequential or incidental damages of any kind relating to or resulting from the use of the Glass Configurator.